

End-Grain Sealing Wax

Technical Data Sheet

January 2020

Page 1/1



- » protects front and cutting edges against cracking and moisture
- » for all decking wood
- » dirt repellent
- » extremely water repellent

Product characteristics:

SAICOS End-Grain Sealing Wax prevents hair-cracking of front edges and bleeding of wood ingredients. It protects the front and cutting edges against cracking and moisture and is strongly water repellent.

Colour:

8131 Colourless

Fields of application:

All front and cutting edges of decking.

Preparation:

The surface must be clean and free from grease and dust. Stir well before use. SAICOS End-Grain Sealing Wax is a final coat and can not be over-coated. If thickened by cold temperatures, warm container slightly up in warm water.

Processing:

Apply SAICOS End-Grain Sealing Wax with a cloth or sponge on the cutting edge in order to create a slight wax film.

Best processing temperature:

between 8° C and 35° C

Coverage per liter:

approx. 14 m² on sawn wood
Depends on wood species and surface structure.

Number of treatments:

1x SAICOS End-Grain Sealing Wax

Drying time:

Touch-dry after approx. 1 hour.
Completely dry – depending on air humidity - after approx. 24 hours.

Cleaning of tools:

with SAICOS Brush Cleaner

Storage:

At least 5 years in sealed container. The liquid product is not susceptible to frost. To restore good spreadability after exposure to frost, store at room temperature for several hours and stir well.

Physical properties:

Density: 0.85 - 0.91 g/cm³

Odour: faint/mild, odourless when dry

Flashpoint: > 61° C acc. to DIN 53213

Safety instructions - first aid:

Keep out of the reach of children. Do not fill into food, beverage or other containers used for foodstuffs. Wash out any product-soaked rags immediately or store in an airtight container (danger of combustion). The dried coating is normally inflammable acc. to EURO norm EN 13501 (DIN 4102 B2).

Safety data sheet available on request.

EU limit for one component special lacquers (cat. A/i): 500 g/l (2010).

SAICOS End-Grain Sealing Wax contains maximum 500 g/l VOC. GGVSEB / ADR -/-

Our application advice is provided to the best of our knowledge and based on experiments, however, applies only as a non-binding recommendation and does not exempt you from testing the products supplied by us as to their suitability for the intended purpose. Since the application and processing of the products is beyond our control, the responsibility rests solely with the user. With publishing a new technical data sheet the previous loses its validity.

SAICOS COLOUR GmbH

Carl-Zeiss-Str. 3

D-48336 Sassenberg

☎ +49 2583 3037-0

☎ +49 2583 3037-10

✉ info@saicos.de

www.saicos.de