



• BAUSTOFFPRÜFSTELLE Wismar GmbH • LÜBSCHER STRASSE 109 • 23966 WISMAR •

SAICOS COLOUR GmbH
 Carl-Zeiss-Straße 3
 48336 Sassenberg

Wismar, 05.09.2013
 our signatur: Ha.

Test report no.:	1971/13
Customer:	SAICOS COLOUR GmbH
Subject matter:	Testing accordance - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test according to DIN 51130:2010-10
Subject date:	28.08.2013
Samples received:	29.08.2013
test date:	05.09.2013
Name of the product:	wood pattern with coating Dimensions l/w [mm]: 100 x 50
surface area:	applied with premium hartwachsoil in gloss 3200 satin finish
Number of samples:	1 tiles
Origin:	as customer
Sampling:	The samples were provided by the customer.

The test report comprises 2 pages

The test results related exclusively to the subject matter that was tested. The test report may not be copied, passed on th third parties or published in extracts without the written consent of BPS Wismar.

Determination of the anti-slip property according to DIN 51130:2010-10 "Testing of floor coverings - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test

Description of the panel:

The brown wood flooring has a slightly woody structure, level surface.

Preparation of the test cover:

A test cover, size 100 x 50 cm was seamlessly produced by laying on a self-supporting, non-warping panel by the customer.


The cover was cleaned with a dry cloth before the start of the test.

Mean angle of inclination:


Test no.	Corrected overall angle of acceptance DIN 51 130 increased skid risk [°]
1	7,2
2	7,3
3	7,7
4	7,7
5	7,5
6	8,2
Mean value	7,6
Mean angle of inclination for assessment group shown below:	6 - 10

Assessment group:

In accordance with the test results obtained pursuant to the guidelines of DIN 51130;
the tiles are to be classified in assessment group **R 9**.


Dipl.-Ing.(FH) Ch. Hartig
Official in Charge




Dipl.-Ing. E. Stoige
Director of the Test Office