

Additive Slow Down

Technical Data Sheet

June 2022

Page 1/1



- » *additive for [2K PU Elastic](#)*
- » *prolongs the workability of the lacquer*
- » *for design floors, PVC and linoleum*

Product characteristics:

Extends processing time of lacquer depending on climatic conditions. Especially recommended when having critical side conditions with high temperatures and low air moisture.

DIBt approval: Z-157.20-208.

Anti-Slip R9.

For professional use only.

Item-Nr.:

9619

Fields of application:

We recommend the application for linoleum, PVC and CV floor coverings with smooth or slightly textured, as well as factory PU-coated floor coverings. The suitability for renovation of safety-relevant floors must be clarified in advance for each property.

Please also see current technical data sheet of [SAICOS 2K PU Elastic](#).

Processing:

Pour the component into [SAICOS 2K PU Elastic](#) and shake well two minutes. Let rest for 5 minutes and shake new. Immediately apply with [SAICOS Aqua-Roller](#).

For partial quantities:

Mix [SAICOS 2K PU Elastic](#) with [SAICOS Hardener 2K 10:1](#) by adding the hardener to the [SAICOS 2K PU Elastic](#). Process ready-mixed product within the pot life of 1-1.5 hours. When mixing partial quantities, observe the recommended mixing ratio (1:10).

Important: Do not close container which contains mixture.

Switch off the underfloor heating 36 h before application.

Switch it back on 24 h after applying the last coat..

Coverage:

Application with [SAICOS Aqua Roller](#),

Application quantity 80 - 120 g / m².

0.45 liter of supplement for 4.55 liter [SAICOS 2K PU Elastic](#).

5 liters are sufficient for about 50 m² (one coat).

Coverage depends on surface structure.

Storage:

In unopened/sealed container at least 1 year. The liquid product is not susceptible to frost.

Safety Instructions – First Aid:

Keep out of the reach of children. Do not fill into food, beverage or other containers used for foodstuffs. Causes serious eye irritation. Wash hands thoroughly after handling. Wear protective gloves and eye/face protection. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. If eye irritation persists: Get medical advice/attention.

EU limit for two component coating (Cat A/j): 140 g / l (2010)

[SAICOS 2K PU Elastic](#) with [Additive Slow Down](#) contains max. 140 g / l VOC.

Our application advice is provided to the best of our knowledge and based on experiments, however, applies only as a non-binding recommendation and does not exempt you from testing the products supplied by us as to their suitability for the intended purpose. Since the application and processing of the products is beyond our control, the responsibility rests solely with the user. With publishing a new technical data sheet the previous loses its validity.

SAICOS COLOUR GmbH

Carl-Zeiss-Str. 3

D-48336 Sassenberg

☎ +49 2583 3037-0

☎ +49 2583 3037-10

✉ info@saicos.de

www.saicos.de