

Ecoline Additive Pure

Technical Data Sheet

June 2022

Page 1/1



Ecoline



- » Additive for our [Ecoline MultiTop^{plus} System](#)
- » perfectly protected surface
- » looks almost as if untreated

Product characteristics:

For producing an almost perfectly protected wood surface that looks as if untreated. DIBt approval Z.157.10-162.

Article number:

9933Eco Pure

Fields of application:

For all wood and bamboo floors (solid wood flooring, parquet, and multi-layer flooring) and interior surfaces. We recommend painting on light, European wood species. Trial coating recommended.

Please also have a look at the Technical Data Sheet [Ecoline MultiTop^{plus} System](#) for further technical information.

Preparation:

Switch off the underfloor heating 36 h before application. Switch it back on 24 h after applying the last coat.

Hint: Do not pour *Additive Ecoline Pure* directly on the surface; rather work with a Paint Tray. Pour additive into [Ecoline MultiTop](#) lacquer and shake well two minutes. Let rest for 5 minutes and shake new.

First coat:

Apply [Ecoline MultiTop](#) with *Additive Ecoline Pure* rapidly with [SAICOS Aqua Roller](#).

Application quantity: approx. 100 - 120 g/sqm.

Drying time: approx. 3 - 4 hours.

Second coat:

Apply [Ecoline MultiTop](#) with *Additive Ecoline Pure* rapidly with [SAICOS Aqua Roller](#).

Application quantity: approx. 100 - 120 g/sqm.

Drying time: approx. 3 - 4 hours.

Important: Maximum two lacquer coats per day.

In-between-sanding: after 6 hours with 120 - 150 grit, remove sanding dust with dry cloth or vacuum cleaner.

Third coat: Depending on the result either use [Ecoline MultiTop](#) with *Additive Ecoline Pure* or [Ecoline MultiTop](#) clear. Apply rapidly with the [SAICOS Aqua Roller](#).

Application quantity: 100 - 120 g/sqm.

Drying time: approx. 8 hours

Coverage:

Application with [SAICOS Aqua Roller](#), Application quantity 100 - 120 g/sqm. 0,45 liter of supplement for 4,55 liter [Ecoline MultiTop](#). 5 liters are sufficient for about 45 sqm (one coat).

Coverage depends on wood species and surface structure.

Storage: In unopened / sealed container at least 1 year. The liquid product is susceptible to frost. Frost-free transport and store (> 5 °C).

Safety Instructions – First Aid:

Keep out of the reach of children. Do not fill into food, beverage or other containers used for foodstuffs.

Contains: TMDD, CIT/MIT (3:1). May produce an allergic reaction. Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

Safety data sheet available on request.

EU limit for two component lacquer (Cat A/j.): 140 g/l (2010)
SAICOS Ecoline MultiTop with supplement *Additive Ecoline Pure* contains max. 140 g/l VOC.

Our application advice is provided to the best of our knowledge and based on experiments, however, applies only as a non-binding recommendation and does not exempt you from testing the products supplied by us as to their suitability for the intended purpose. Since the application and processing of the products is beyond our control, the responsibility rests solely with the user. With publishing a new technical data sheet the previous loses its validity.

SAICOS COLOUR GmbH

Carl-Zeiss-Str. 3

D-48336 Sassenberg

☎ +49 2583 3037-0

☎ +49 2583 3037-10

info@saicos.de

www.saicos.de